



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R4032

MARINITE A

This thermal treated board has excellent resistance to thermal shock and good stability at high temperatures. It is used for conveying, containing and forming molten aluminum and other non-ferrous metals. Its higher strength makes it easier to machine.



APPLICATIONS

- Holding furnace linings
- Tips for continuous casters
- Transition plates
- Rings
- Plugs
- Baffles
- Troughs
- Spouts
- Floats
- Filter boxes

SPECIFICATIONS

Technical Data

Density	65lbs/ft³ (1041kg/m³)
Modulus of Rupture (Flexural Strength)	1400psi (98kg/cm²)
Ultimate load	3000psi (211kg/cm²)
Load @ 5% deformation	2400psi (169kg/cm²)
Moisture Content (normal), % of dry weight	2.5
Thermal Conductivity (Btu-in/ft ² , hr, °F)	800°F: 1.92, 1000°F: 1.95
Thermal Conductivity (W/m ² K)	427°C: 0.28, 538°C: 0.28
Shrinkage 24h at 1350°F	Linear: 0.1%, Thickness: 0.8%

Screw Holding Strength @ 7/8" penetration	240lbs (109kg)
--	-----------------------

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.