



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R4041

MARINITE CF

This insulating board is made of calcium silicate reinforced of carbon fibers.



APPLICATIONS

It is a clear choice for transition plates in continuous aluminium castings of T-ingots and billets.

SPECIFICATIONS

Technical Data

Density	50 pcf
Temperature	800°C (1472 °F)
Shrinkage 24 hours at 732°C (1350 °F)	
Thickness	0.98%
Linear	0.50%
Moisture	2.0%

N.B. The information, details and values indicated are to the best of our knowledge. We recommend to conduct tests according to local conditions. The data is subject to some variations without notice.