



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R4055

MARINITE M

These oven dried boards are used in a variety of heat insulating processes, fire protection and machined parts. The selection is commonly based on a balance between strength and insulating qualities.



APPLICATIONS

Principal applications : oven walls and linings, welding insulation, fire doors, fire training burn buildings, cable trays, personnel protection, and as insulation for marine ships and off-shore rigs.

Back-up insulation applications : ladles, torpedo cars and tundishes in the iron and steel industry, lime and cement plant rotary kilns, and aluminium die cast holding furnaces.

SPECIFICATIONS

Technical Data

Density lbs ft³ (kg/m³)	46 (737)
Modulus of Rupture (Flexural Strength) psi (kg/cm²)	800 (56)
Compressive Strength	
Ultimate load psi (kg/cm ²)	-
@ 5% deformation psi (kg/cm ²)	1000 (70)
Moisture Content (normal), % of dry weight	3.0
Thermal Conductivity	
Mean Temperatre, Btu-in/ft ² , hr, °F	
• 250°F	-
• 400°F	0.81
• 600°F	0.79

• 800°F	0.81
• 1000°F	0.86
Mean Temperature, (W/m ² K)	
• 121°C	-
• 204°C	0.12
• 316°C	0.11
• 427°C	0.12
• 538°C	0.12
Shrinkage 24 hours at 649°C (1200°F)	
Linear (Length or width), %	0.4
Shrinkage 24 hours at 649°C (1200°F)	
Thickness, %	1.4
Electrical	
Arc Resistance, seconds, ASTM D 495	-
Volume Resistivity, ohm-cm, ASTM D 257	9.8 X (10 ⁷)
Dielectric Strength, v/mil, ASTM D 495	45
Screw Holding Strength	
@7/8" penetration, lbs (kg)	200 (91)

N.B. The information, details and values indicated are to the best of our know ledge. We recommend to conduct tests according to local conditions. The data is subject to some variations w ithout notice.