



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R813

RUBBER

The 3R813 is made of a premium quality natural rubber and offers various application possibilities. It however, has a poor resistance to ozone and aromatic hydro-carbons.



APPLICATIONS

This rubber is often used in areas where flexibility and abrasion resistance are required.

SPECIFICATIONS

Technical Data

Polymer Type	Natural NR
Color	Tan
Hardness (Shore A) ± 5	40
Temperature	-25°C to 80°C (-10°F to 180°F)
Tensile Strength, lbs/in²	2500
Elongation minimum, %	400
Compression Set	Excellent
Abrasion Resistance	Excellent
Tear Resistance	Very Good
Ozone Resistance	Poor
Impermeability to Gases	Good
Resistance to Dilute Acid	Fair to Good
Resistance to aromatic hydro-carbons	Poor
Heat Aging	Fair

N.B. The information, details and values indicated are to the best of our knowledge. We recommend to conduct tests according to local conditions. The data is subject to some variations without notice.