



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R825

RUBBER

This black SBR contains one or two synthetic fabric layers, which makes it long lasting and more resistant than the 3R820.



APPLICATIONS

Gaskets for air, hot and cold water and low pressure steam
Static applications

SPECIFICATIONS

Technical Data

Polymer	Styrene-Butadiene (SBR)
Reinforcement fabric	Polyester 2 oz.
Specific gravity	1.51 gr/cc
Color	Black
Hardness (Shore A) (ASTM D2240)	80 ± 5
Temperature	-29°C to 82°C (-20°F to 180°F)
Tensile, psi (ASTM D412)	500 min.
Ultimate Elongation, % (ASTM D412)	100 min.
Compression Set	22 hrs @ 70C (158F): 50% max.
Heat Aging (ASTM D573)	70 hrs @ 70C (158F) - Changed: Hardness: +/- 15 points max., Tensile: +/- 30% max., Elongation: -50% max.
Abrasion Resistance	Good
Tear Resistance	Good
Ozone Resistance	Fair
Impermeability to Gases	Fair

Resistance to Dilute Acid	Poor
Resistance to aromatic hydro-carbons	Poor
Heat Aging	Fair

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.