



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R833

RUBBER

This material is known for its use in applications in temperatures reaching 455°F.



APPLICATIONS

The grey 3R833 has the additional properties of flame retardant, electrical stability, ozone and ultra violet resistance to make it the unique product for numerous applications.

SPECIFICATIONS

Technical Data

Polymer Type	Silicone
Color	Grey
Hardness (Shore A) ± 5	60
Temperature	-65°C to 250°C (-85°F to 480°F)
Tensile Strength, psi (ASTM D-412)	700
Elongation minimum, % (ASTM D-412)	300
Tear, psi Die "B" (ASTM D-624)	40
Compression Set	Very good
Ozone Resistance	Excellent
Fungus resistance	Good

N.B. The information, details and values indicated are to the best of our knowledge. We recommend to conduct tests according to local conditions. The data is subject to some variations without notice.

