



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R846

RUBBER

This black nitrile rubber is efficient and still maintains its flexibility in temperatures ranging -34°C to 88°C (-30°F to 190°F). This product has a excellent resistance to petroleum-based hydraulic fluids and a very good resistance to alkalis and acids.



APPLICATIONS

The 3R846 is an ideal material for applications in environments where there are concentrations of gas, oil, grease or solvents.

SPECIFICATIONS

Technical Data

Polymer	Nitrile blend (NBR/SBR)
Color	Black
Specific Gravity	1.34 gr/cc
Hardness (Shore A) (ASTM D2240)	60
Temperature	-34°C to 88°C (-30°F to 190°F)
Tensile Strength, psi (ASTM D412)	1000 min.
Ultimate Elongation, % (ASTM D412)	350 min.
Compression Set (ASTM D395B)	22 @ 100°C 40% max.
Heat Aging (ASTM D573)	70 hrs @ 100°C: Changed: Hardness +/- 15 pts max., Tensile +/- 30% max., Elongation -50% max.
Oil aging #3 (ASTM D471)	70 hrs @ 100°C - Volume changed: 80% max.

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.

