

### industries3r.com

### Danville office

Industries 3R inc. 55, Road 116 West Danville (Quebec) Canada J0A 1A0

Telephone: (819) 839-2793 Fax: (819) 839-2797 Toll-free: (800) 567-2728 Email: info@industries3r.com

#### Montreal office

Industries 3R inc. 1479, Begin street Ville St-Laurent (Quebec) Canada H4R 1V8 Telephone: (514) 333-3971 Fax: (514) 333-7224 Email: info@industries3r.com

# 3R846 RUBBER

This black nitrile rubber is efficient in temperatures ranging  $-22^{\circ}$ F to  $185^{\circ}$ F and still maintains its flexibility.



## **APPLICATIONS**

The 3R846 is an ideal material for applications in environments where there are concentrations of gas, oil, grease or solvents.

## **SPECIFICATIONS**

### **Technical Data**

Polymer Type	Nitrile NBR
Color	Black
Hardness (Shore A) ± 5	60
Temperature	-30°C to 85°C (-30°F to 185°F)
Tensile Strength, lbs/in²	1000
Elongation minimum, %	350
Compression Set	Good
Abrasion Resistance	Good
Tear Resistance	Fair
Ozone Resistance	Poor
Impermeability to Gases	Excellent
Resistance to Dilute Acid	Good
Resistance to aromatic hydro-carbons	Good
Heat Aging	Very Good

N.B. The information, details and values indicated are to the best of our know ledge. We recommend to conduct tests according to local conditions. The data is subject to some variations w ithout notice.