



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office


Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R856

RUBBER

3R856 is a Viton® grade A rubber with good resistance to chemicals such as oils, fuels, lubricants and most mineral oils. It withstands operating temperatures over 200°C (400°F). It can also be easily used outdoors because it is resistant to bad weather, atmospheric oxidation, UV rays, ozone, fungi and mold.



APPLICATIONS

The composition of 3R856 ensures a very good seal in aggressive environments. For example, it is ideal for the manufacture of seals in applications in the presence of petroleum products.

SPECIFICATIONS

Technical Data

Polymer Type	Fluorelastomer (FKM)
Color	Black
Hardness (Shore A) ± 5	75
Operation temperatures	-28°C à 205°C (-20°F à 400°F)
Tensile Strength, psi	1200
Elongation minimum, %	165

N.B. The information, details and values indicated are to the best of our knowledge. We recommend to conduct tests according to local conditions. The data is subject to some variations without notice.