



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R887M

GRAPHITE SHEETS

The 3R 887M is a flexible graphite sheet reinforced with a 0.0005" thick Mylar film. This sheet is made from exfoliated graphite flakes which is compressed into a foil by a carefully controlled calendaring process. In this process, the expanded flake particles are mechanically locked together without the use of fibers, binders or other additives. Sheets of foil are then adhesively bonded and laminated to the required thickness.



APPLICATIONS

The 3R 887M flexible graphite sheet has pressure-temperature sealing capabilities that are far superior to all asbestos and non-asbestos reinforced sheet products. It is resistant to chemical attacks by virtually all organic and inorganic fluids with the exception of concentrated, highly oxidizing acids.

Gaskets cut from this sheet seal low to moderate bolt loads and because of its very low creep relaxation, re-torquing is rarely required. Flexible graphite readily flows into flange irregularities enabling it to seal both smooth and coarse surface finishes.

SPECIFICATIONS

Service limits

Temperature Limits	
Maximum	
• In air	-240 °C à 510 °C (-400 °F à 950 °F)
• Mild oxidizing environnement	-240 °C à 850 °C (-400 °F à 1500 °F)
• Non oxidizing environnement	up to 980 °C (up to 1 800 °F)
Physical Properties	
Compressibility (ASTM F-36)%	44
Recovery (ASTM F-36)%	15
Creep Relaxation (ASTM F-38)	Less than 5%
Chemical Composition	
Carbon Content	99% Minimum

Ash	0.8% Maximum
Leachable chloride	30 ppm maximum
Available Sheet Sizes	
Thickness	1/32", 1/16", 1/8"
Sheet Sizes	39.4" X 39.4", 60" X 60 "

N.B. The information, details and values indicated are to the best of our know ledge. We recommend to conduct tests according to local conditions. The data is subject to some variations w ithout notice.