



[industries3r.com](http://industries3r.com)

**Danville office**

Industries 3R inc.  
55, Road 116 West  
Danville (Quebec)  
Canada J0A 1A0

Telephone: (819) 839-2793  
Fax: (819) 839-2797  
Toll-free: (800) 567-2728  
Email: [info@industries3r.com](mailto:info@industries3r.com)

**Montreal office**

Industries 3R inc.  
1479, Begin street  
Ville St-Laurent (Quebec)  
Canada H4R 1V8

Telephone: (514) 333-3971  
Fax: (514) 333-7224  
Email: [info@industries3r.com](mailto:info@industries3r.com)

## NEMA G9

The G9 is a woven glass fabric combined with a melamine resin laminate. It is a very hard, flame resistant machining grade with excellent electrical properties in high humidity conditions. This material also has high physical strength and excellent arc resistance. Maximum temperature : 284°F.



## APPLICATIONS

It is used to make switchboard panels, arc barriers, circuit breaker parts and structural/electrical components.

## SPECIFICATIONS

### Technical Data

Specific gravity	1.85
Tensile strength (psi)	44 000 / 34 000
Flexural strength (psi)	61 100
Compressive strength (psi)	70 000
Hardness, M Scale	115
Bonding strength (lbs)	1900
Shear strength (psi)	18.000
Dissipation factor @ 1 MHz	0.015
Electric strength - volt / 1000	540
Flammability rating	V-O
Temperature	140 °C (284°F)
Coeff. Thermal Exp. In/In/°C x 10 <sup>-6</sup>	15
Water absorption %	0.6

---

**N.B.** The information, details and values indicated are to the best of our knowledge. We recommend to conduct tests according to local conditions. The data is subject to some variations without notice.