



[industries3r.com](http://industries3r.com)

**Danville office**

Industries 3R inc.  
55, Road 116 West  
Danville (Quebec)  
Canada J0A 1A0

Telephone: (819) 839-2793  
Fax: (819) 839-2797  
Toll-free: (800) 567-2728  
Email: [info@industries3r.com](mailto:info@industries3r.com)

**Montreal office**

Industries 3R inc.  
1479, Begin street  
Ville St-Laurent (Quebec)  
Canada H4R 1V8

Telephone: (514) 333-3971  
Fax: (514) 333-7224  
Email: [info@industries3r.com](mailto:info@industries3r.com)

## SG200

The SG200 is polyester glass laminate that has excellent retention of mechanical properties at high temperatures of 410°F.



### APPLICATIONS

It is the ideal material for the power combs of dry-type transformers.

### SPECIFICATIONS

#### Technical Data

Specific gravity (ASTM D-792)	<b>1.7</b>
Tensile strength (ASTM D-638) (psi)	<b>12 500</b>
Flexural strength (ASTM D-790) (psi)	<b>29 000</b>
Compressive strength (ASTM D-695) (psi)	<b>36 000</b>
Shear Strength (ASTN_D732) (psi)	<b>11 100</b>
Water absorption, 24 hours %	<b>0.3</b>

**N.B.** The information, details and values indicated are to the best of our knowledge. We recommend to conduct tests according to local conditions. The data is subject to some variations without notice.