



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

STOP IT

STOP IT

The STOP IT pipe repair system repairs carbon steel, stainless, aluminium, copper, galvanized, PVC, CPVC, PVDF, polyethylene, polypropylene, and fiberglass pipes. The repair, very rapid, dries in 30 minutes. It requires only one person and no special tools.

The kit contains a knitted fiberglass tape coated with a special urethane resin that is water-activated, which is ideal for repair of pipe leaks and reinforcing pipe joints in any situation, even under water.



APPLICATIONS

Generally, STOP IT® may be used with products that are compatible with polyurethane plastic. The durability of the repair may be affected by strong acids or bases.

As for its chemical resistance, there is no visible changes in STOP IT® after an immersion term of 35 days in the following chemicals: Acetic Anhydride, Ammonia, Ammonium Hydroxide (10%), Diesel Fuel, Ethylene Glycol, Gasoline, Hydrochloric Acid (10%), Lube Oil, Mineral, Spirits, Sodium Hydroxide (50%), Sulfuric Acid (10%), Sulfuric Acid (25%), Varsol.

Concerning the safety, even under extreme pressures, the STOP IT® will not shatter or crack and releases pressures slowly.

SPECIFICATIONS

Physical properties

Shelf Life	Two years from date of purchase when stored at 40°F to 83°F (5°C to 28°C)
Color	White
Tensile strength (ASTM D 638-111)	3920 psi (275 kg/cm²)
Bond strength (ASTM D 2095-72)	230 psi (16 kg/cm²) average
Flexural strength (ASTM D 790-1-B)	2260 psi (159 kg/cm²)
Durometer Hardness (ASTM D-2240)	82 (Shore D)
Pressure Retaining Capability	Recommended for pressures up to 400 psi (28 kg/cm²)
Temperature resistance	
Continuous	-25°C to 120°C (-10°F to 245°F)
Intermittent	120°C to 260°C (245°F to 500°F)

N.B. The information, details and values indicated are to the best of our knowledge. We recommend to conduct tests according to local conditions. The data is subject to some variations without notice.