

industries3r.com

Danville office

Industries 3R inc. 55, Road 116 West Danville (Quebec) Canada J0A 1A0

Telephone: (819) 839-2793 Fax: (819) 839-2797 Toll-free: (800) 567-2728 Email: info@industries3r.com

Montreal office

Industries 3R inc. 1479, Begin street Ville St-Laurent (Quebec) Canada H4R 1V8 Telephone: (514) 333-3971 Fax: (514) 333-7224 Email: info@industries3r.com



These ropes are made from fiberglass yarns of 6 to 9 microns in diameter. They are strong, soft, flexible and resist temperatures up to 1000°F. They are suitable for numerous applications including dry sealing and fire protective uses.



APPLICATIONS

The TXP300 glass fiber insulating ropes are used for insulating, sealing and caulking high temperature pipes and equipment. The steel mills, foundries, aluminum plants as well as mechanical contractors fully appreciate their advantages to seal pipes and joints particularly in hard to reach places.

SPECIFICATIONS

Technical Data

Temperature	535°C (1000°F)
Diameter	5/16", 3/8", 1/2", 3/4, 1", 2"
Standard roll length	100 feet (30 meters)
Thermal Conductivity (k) W/(mK) (1/2" dia. Rope)	0.055 - 0.065

N.B. The information, details and values indicated are to the best of our know ledge. We recommend to conduct tests according to local conditions. The data is subject to some variations without notice.