



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R2300

CERAMIC

The ceramic fiber blankets are produced from exceptionally pure oxides of alumina and silica using the spinning process. The 3R2300 is flexible and stays stable at high temperatures which makes it an excellent choice for insulation. It is also recommended as a refractory support.



APPLICATIONS

The ceramic fiber blanket applications are numerous. It is used as insulation for furnaces, boiler combustion chambers, heat exchangers, gas turbines and high temperature fans, as removable insulating pads on steam valves and separators. It can also be used to fabricate insulating mats for superheated seals, stress relief pads and expansion joints. The 3R2300 is especially recommended for those applications requiring a low iron content of less than 1% and for highly reducing atmospheres.

SPECIFICATIONS

Technical Data

Color	White
Density, lbs/ft ³ (kg/m ³)	4, 6, 8 (64, 96, 128)
Thickness, in. (mm)	1/4 - 2 (6.25 - 50)
Continuous use limit	1 175 °C (2145 °F)
Temperature maximum	1 315 °C (2395 °F)
Melting point, °F (°C)	1 760 °C (3200 °F)
Chemical Analysis, Nominal %	
Alumina, Al ₂ O ₃	46
Silica, SiO ₂	54
Ferric oxyde, Fe ₂ O ₃	0.05
Thermal conductivity, BTU-in/hr-ft ² - °F (w/m.k), ASTM C201	
Mean Temperature - 500°F (260°C)	
• 4 pcf	0.54 (0.08)

• 6 pcf	0.47 (0.07)
• 8 pcf	0.44 (0.06)
Mean Temperature - 1000°F (538°C)	
• 4 pcf	1.34 (0.19)
• 6 pcf	1.06 (0.15)
• 8 pcf	0.93 (0.13)
Mean Temperature - 1500°F (816°C)	
• 4 pcf	2.48 (0.36)
• 6 pcf	1.90 (0.27)
• 8 pcf	1.60 (0.23)
Mean Temperature - 1800°F (982°C)	
• 4 pcf	3.23 (0.47)
• 6 pcf	2.45 (0.35)
• 8 pcf	2.05 (0.30)
Mean Temperature - 2000°F (1093°C)	
• 4 pcf	3.74 (0.54)
• 6 pcf	2.83 (0.41)
• 8 pcf	2.34 (0.34)

N.B. The information, details and values indicated are to the best of our knowledge. We recommend to conduct tests according to local conditions. The data is subject to some variations without notice.