



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R782

EG2

The 3R782 is made of an aramid core covered with graphite particles and completely coated with a PTFE jacket and has a high temperature break-in lubricant treatment. The aramid core gives it excellent mechanical strength and dimensional stability, while the PTFE/graphite jacket provides chemical resistance, heat conductivity and a low coefficient of friction.



APPLICATIONS

This packing is suited for corrosive applications. Its high resistance to extrusion (four times higher than conventional PTFE/graphite packings) makes it ideal for handling chemically aggressive fluids in high surface speed and high pressure applications.

SPECIFICATIONS

Technical Data

| | |
|-------------|--|
| Temperature | -100°C to 280°C (-148°F to 536°F) |
| Pressure | Static:3600psi (250 bar), Rotating: 500psi (35 bar), Reciprocating: 3600psi (250 bar) |
| Shaft Speed | 4921 fpm (25 m/s) |

Service limits

| | |
|----|-------------|
| pH | 0-14 |
|----|-------------|

Approximate yields - Feet per pound (+/- 10%)

| | |
|-------|-------------|
| 3/16" | 36.9 |
| 1/4" | 21.6 |
| 5/16" | 13.7 |

| | |
|-------|-----|
| 3/8" | 9.2 |
| 7/16" | 8.4 |
| 1/2" | 5.6 |
| 9/16" | 4.5 |
| 5/8" | 3.6 |
| 3/4" | 2.5 |
| 7/8" | 2.0 |
| 1" | 1.5 |

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.