



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R8100

TEALON

The 3R8100 is produced from virgin PTFE resin filled with micro spheres of Barium Sulfate. This unique process of fabrication provides the Tealon® a high level of fibrillation to overcome the creep relaxation and cold flow problems associated with mechanical grade (3R810) and virgin grade (3R812) PTFE sheets. It is FDA approved.



APPLICATIONS

- Food industry
- Strong caustics
- Moderate acids
- Chlorine
- Gases
- Water
- Steam
- Hydrocarbons
- Hydrogen
- Aluminum fluoride

SPECIFICATIONS

Technical Data

| | |
|---|-----------------------------------|
| Sheet size | 60"X60" |
| Thickness | 1/16" and 1/8" |
| Color | Off-white |
| PH | 0 - 14 |
| Pressure | 1200 psi (83 bar) |
| Temperature | -268°C to 260°C (-450°F to 500°F) |
| PxT factor (psi x °F) | 1/16": 350 000, 1/8": 250 000 |
| Compressibility Range @ 5000 psi (ASTM F-36A) | 4-10% |
| Recovery @ 5000 psi (ASTM F-36A) | 40% |

| | |
|--|--|
| Creep Relaxation (ASTM F-38B) | 15% |
| Specific Gravity (ASTM D-792) | 2.90g/cm³ |
| Tensile strength (ASTM F-152) | 2030psi |
| Sealability (ASTM F-37A) | 0.04ml/h |
| Sealability (DIN 3535) | .015cm³/min |
| Gasket factors m | 1/16" and 1/8": 2 |
| Gasket factors y | 1/16": 1 800psi, 1/8": 1 500psi |
| Gasket factors - Force maximale Sgmax | 1/16": 20 000psi, 1/8": 14 500psi |

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.