


industries3r.com
Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R815

RUBBER

This premium quality neoprene rubber offers a moderate protection against oil, ozone and ultraviolet, and has a good impermeability to gas. It is available in three different hardness.



APPLICATIONS

The 3R815 is commonly used as flange gasketing and as static joints. It is also used in applications where the material is in contact with harsh atmospheric conditions.

SPECIFICATIONS

Technical Data

Polymer	CR/SBR/NBR
Specific Gravity	1.32 gr/cc
Color	Black
Hardness (Shore A) (ASTM D2240)	60
Temperature	-29°C to 88°C (-20°F to 190°F)
Tensile, psi (ASTM D412)	1000 min.
Ultimate elongation, % (ASTM D412)	300 min.
Compression Set	22h @ 100C (212F): 80% max.
Heat Aging (ASTM D573)	70h @ 100C (212F): Changed - Hardness: +/-15 points max., Tensile: +/- 30% max., Elongation: -50% max.
Oil Aging #3 (ASTM D471)	70h @ 100C (212F): Volume changed: 120% max.
Abrasion Resistance	Very Good
Tear Resistance	Good
Ozone Resistance	Fair
Impermeability to Gases	Good

Resistance to Dilute Acid	Good
Resistance to aromatic hydro-carbons	Fair
Heat Aging	Good

ASTM D2000 - 1BC610

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.