


industries3r.com
Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R818

RUBBER

This rubber is made with one or four thicknesses of polyester fabric inserted in a premium quality neoprene. The 3R818 combines the oil and ozone resistance to resistance of the synthetic fabric. It offers exceptional tensile strength.



APPLICATIONS

Gaskets for control valves and regulators
Cold barriers

SPECIFICATIONS

Technical Data

Polymer	Neoprene, Styrene-Butadiene (CR/SBR)
Fabric	Nylon 14 oz.
Color	Black
Specific Gravity	1.58 gr/cc
Hardness (Shore A) (ASTM D2240)	70
Tensile, psi (ASTM D412)	1400 min.
Ultimate Elongation, % (ASTM D412)	250 min.
Temperature	-29°C to 100°C (-20°F to 212°F)
Compression Set (D395B)	22 hrs @ 100C (212F): 35% max.
Heat Aging (ASTM D573)	70 hrs @ 100C (212F) - Changed: Hardness + 15 points max., Tensile -15% max., Elongation -40% max.
Oil Aging #3 (ASTM D471)	70 hrs @ 100C (212F) - Changed: Hardness +/- 10 points max., Tensile: -70% max., Elongation: -55% max., Volume: +120% max.
Abrasion resistance	Good
Tear Resistance	Good

Ozone Resistance	Good
Impermeability to Gases	Good
Resistance to Dilute Acid	Good
Resistance to aromatic hydro-carbons	Good
Heat Aging	Good

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.