



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office



Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

3R875

COMPRESSED SHEETS

Inorganic fibers bonded with nitrile (NBR) compressed sheet used in thermal cycling applications due to his thermal stability. .



APPLICATIONS

Extreme thermal cycling
Saturated and superheated steam
Petroleum derivatives
Ethanol

SPECIFICATIONS

Technical Data

| | |
|---|---|
| Color | Black |
| Temperature | Continuous: 430°C (806 °F), Short term: 550°C (1022 °F) |
| Pressure | Continuous: 1480 psi, Short term: 2177 psi |
| Density | 1/16": 91.14 lb/ft³ (1.46 g/cm³) |
| Compressibility (ASTM F36A) | 1/16": 12-22% |
| Recovery (ATM F36 J) | 40% min. |
| Tensile strength across grain (ASTM F152) | 1305 psi (9 N/mm²) |

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.