



industries3r.com

Danville office

Industries 3R inc.
55, Road 116 West
Danville (Quebec)
Canada J0A 1A0

Telephone: (819) 839-2793
Fax: (819) 839-2797
Toll-free: (800) 567-2728
Email: info@industries3r.com

Montreal office

Industries 3R inc.
1479, Begin street
Ville St-Laurent (Quebec)
Canada H4R 1V8

Telephone: (514) 333-3971
Fax: (514) 333-7224
Email: info@industries3r.com

TXP423

NEOPRENE COATED FIBERGLASS

The yellow TXP 423 is incombustible, resists slagging, to sparks and incidental flames from cutting torches.



APPLICATIONS

This fabric is recommended for the use in vertical welding curtains and protection clothing such as aprons, mitts, leggings and gauntlets.

SPECIFICATIONS

Technical Data

Weight (ASTM-D-3776)(oz/sy²)	23
Thickness (ASTM D-1777)	0.034"
Tensile strenght (ASTM D-5587)	Warp : 200 lbs Fill: 200 lbs
Tear strength (ASTM D-5587)	Warp : 45 lbs Fill: 35 lbs
Burst strength (ASTM D-3786) (psi) (psi)	340
Temperature	-40°C to 150°C (-400°F to 300°F)

N.B. The information, details and values indicated are to the best of our know ledge. We recommend to conduct tests according to local conditions. The data is subject to some variations without notice.