


[industries3r.com](http://industries3r.com)
**Danville office**

Industries 3R inc.  
55, Road 116 West  
Danville (Quebec)  
Canada J0A 1A0

Telephone: (819) 839-2793  
Fax: (819) 839-2797  
Toll-free: (800) 567-2728  
Email: [info@industries3r.com](mailto:info@industries3r.com)

**Montreal office**


Industries 3R inc.  
1479, Begin street  
Ville St-Laurent (Quebec)  
Canada H4R 1V8

Telephone: (514) 333-3971  
Fax: (514) 333-7224  
Email: [info@industries3r.com](mailto:info@industries3r.com)

# TXP507A

## TEFLON COATED FIBERGLASS

The TXP507A is a medium-weight woven fiberglass fabric coated with PTFE resin on both sides. It is highly resistant to outdoor conditions, chemicals, and abrasion. It has excellent antistatic properties and outstanding chemical resistance. This fabric is rigid, non-sticky, easy to sew, and easy to clean. It is designed for sealing suspended roofs of oil tanks, sealing chemical storage tanks, dust insulation, and other types of fire control systems.



## APPLICATIONS

- Removable insulation blankets
- Protective sleeves for valves, pumps, flanges
- Protection against frost
- Protection against chemicals

## SPECIFICATIONS

### Technical Data

Base fabric	
Weave	4H Satin
Construction (ASTM D 3775-96)	Warp: 48 ends/inch (18 ends/cm) Weft: 32 picks/inch (12.6 picks/cm)
Weight (ASTM D3776-96)	12.6 oz/yd <sup>2</sup> (430 g/m <sup>2</sup> )
Thickness	0.015" (0.37 mm)
Coated fabric	
Coating	PTFE coated on both sides
Weight (ASTM D3776-96)	18 oz/yd <sup>2</sup> (610 g/m <sup>2</sup> )
Thickness (ASTM D1777-96)	0.017" (0.45 mm)
Color	Black
Fire resistance	Flame retardant
Antistatic	Yes (Static Dissipative)

Temp resistance	Glass fabric: Up to 1000°F (550°C) PTFE coating: Up to 620°F (330°C)
-----------------	---

**N.B.** The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.